

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**

Amendments To The Claims

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently Amended) A process for the preparation of a microencapsulated composition containing at least one lipophilic compounds compound comprising ~~of the following steps:~~

(i) ~~Partiele~~ particle size reduction of the lipophilic compound, in the presence of a surface active agent, to provide a first composition;

(ii) ~~Preparing~~ providing a solution of alkali metal alginate;~~-~~

(iii) ~~Combining~~ combining said first composition and the alkali metal alginate solution solutions of step (i) and step (ii) to provide a second composition;

(iv) ~~Adding~~ adding dropwise the second composition solution obtained from stage (iii) to a solution containing  $\text{Ca}^{2+}$ , thereby obtaining beadlets, and removing the formed beadlets from said solution;

(v) ~~Rinsing~~ rinsing the beadlets with an acidic solution and drying said beadlets to obtain dried beadlets;  
and

(vi) ~~Coating~~ coating the dried beadlets with a coating material obtained from step (v) to obtain the microcapsules containing said lipophilic compound.

2. (Original) A process according to claim 1, wherein the particle size of the lipophilic compound is reduced to a particle size not greater than 20  $\mu\text{m}$ .

3. (Original) A process according to claim 2 wherein the particle size of the lipophilic compound is reduced to a particle size not greater than 10  $\mu\text{m}$ .

4. (Original) A process according to claim 1, wherein the alkali metal alginate is sodium or potassium alginate.

5. (Original) A process according to claim 1 wherein a filler is added to stage (i).

6. (Currently Amended) A process according to claim 1, wherein the lipophilic compound is selected from ~~among a~~ the group comprising consisting of lycopene, beta and alpha-carotene, lutein, astaxanthin, zeaxanthin, vitamin A, vitamin E, vitamin D, omega 3 oils, omega 6 oils and mixtures thereof

7. (Original) A process according to claim 1 wherein a filler is added to stage (ii).

8. (Original) A process according to claim 1, wherein the lipophilic compound containing alginate beadlets are in the size range of 100 to 425  $\mu\text{m}$ .

9. (Currently Amended) A process according to claim 1 wherein the acidic solution is an acidic aqueous solution of ~~comprising of~~ an acid selected from ~~among a~~ the group ~~comprising~~ consisting of citric, aspartic, acetic, ascorbic, lactic, phosphoric ~~or~~ and hydrochloric ~~acid~~ acids.

10. (Currently Amended) A process according to claim 1 wherein the coating material applied in stage (vi) is selected from ~~among a~~ the group ~~comprising~~ consisting of cellulose derivatives, waxes, fats, proteins and polysaccharides.

11. (Original) A process according to claim 10 wherein the cellulose derivative is hydroxypropylcellulose.

12. (Currently Amended) A process according to claim 1 wherein size reduction of ~~step~~ stage (i) is carried out in a liquid medium wherein said liquid medium is water or a water miscible liquid.

13. (Original) A microencapsulated composition comprising of one or more lipophilic compounds enveloped by a surfactant agent, encapsulated in an alginate matrix and further coated with an outer coating, wherein the particle size of the lipophilic substance is not greater than 20  $\mu\text{m}$ .

14. (Currently Amended) A composition according to claim 13 wherein the lipophilic compound is selected from the ~~among a group consisting comprising~~ of lycopene, beta and alpha-carotene, lutein, astaxanthin, zeaxanthin, vitamin A, vitamin E, vitamin D, omega 3 oils, omega 6 oils and mixtures thereof.

15. (Original) A composition according to claim 13 wherein the particle size of the lipophilic compound is not greater than 10  $\mu\text{m}$ .

16. (Original) A composition according to claim 15 wherein the particle size not greater than 5  $\mu\text{m}$ .

17. (Original) A composition according to claim 13 wherein the size of the microcapsules is in the range of 50  $\mu\text{m}$  to 950  $\mu\text{m}$ .

18. (Original) A composition according to claim 17 wherein the size of the microcapsules is in the range of 100  $\mu\text{m}$  to 450  $\mu\text{m}$ .

19. (Original) A composition according to claim 13 comprising 0.1% to 40% of a lipophilic compound or mixtures thereof.

20. (Currently Amended) A composition according to claim 13 wherein the outer coating is of a material selected from the among a group consisting ~~comprising~~ of cellulose derivatives, waxes, fats, proteins and polysaccharides.

21. (Currently Amended) A composition according to claim 19 wherein the outer coating is hydroxypropylcellulose.

22. (Original) A composition according to claim 13 wherein said composition is tablet grade.

23. (Original) A method for incorporating lipophilic compounds in food stuff comprising of encapsulating the lipophilic compound according to the process of claim 1 and adding the encapsulated composition to food stuff.

24. (Original) A method for masking the flavor and/or smell of lipophilic compounds comprising encapsulating the lipophilic compound according to the process of claim 1.

25. (New) A process for preparing a microencapsulated composition containing at least one liquid lipophilic compound, comprising :

(i) particle size reduction of the liquid lipophilic compound, in the presence of a surface active agent, and optimally a filler in a liquid medium of (1) water, (2) a water-miscible liquid, or (3) a mixture of water and a water-miscible liquid, thereby providing a suspension or emulsion wherein the particle size of the lipophilic compound is not greater than 10  $\mu\text{m}$ ;

(ii) providing a solution of an alkali metal alginate optionally containing a filler;

(iii) combining said suspension or emulsion and the solution of alkali metal alginate to provide a second suspension or emulsion;

(iv) adding dropwise the second suspension or emulsion to a solution containing  $\text{Ca}^{2+}$  thereby obtaining beadlets in liquid, said beadlets having a second coating thereon, and removing said beadlets from said liquid;

(v) rinsing said beadlets with an acidic solution and drying said beadlets to obtain dried beadlets;

(vi) coating the dried beadlets with a coating material to provide a third coating, thereby obtaining microcapsules of 100-450  $\mu\text{m}$  in particle size containing said lipophilic compound, wherein said microcapsules comprise said second and third coatings.